



GPRINT 115

Priloka č. 8

Grammage (g/m ²)	70	80	90	100	115	130	150	170	200	250
Opacity (%)	87.5	90.5	92	93.5	96	97	98	98.5	99	99.5
Thickness (µm)	68	77	87	98	113	129	150	172	203	255
Bulk	0.96	0.96	0.97	0.98	0.98	0.99	1.00	1.1	1.2	1.2
Whiteness (CIE)	117	117	117	117	117	117	117	117	119	119
Brightness (ISO 2470)	95	95	95	95	95	95	95	95	97	97
Smoothness (PPS, µm)	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.8	2.2	2.2
Surface Gloss	<25	<25	<25	<25	<25	<25	<25	<25	<30	<30

Permanent document, acid free ISO 9706

Screen recommended, max 175 lpi

FSC, PEFC, ISO 14001, Paper Profile, EMAS

Values are targets only and can be subject to changes over time without prior notice.